

AMENDMENTS TO THE CLAIMS

1. (Currently amended) An absorbent composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata;

the first stratum comprising first fibers

the second stratum comprising second fibers and superabsorbent material;

the third stratum comprising third fibers;

the first transition zone comprising ~~fibers from the first and second strata commingled a~~
substantially uniform mixture of first fibers, second fibers, and superabsorbent material, the
transition zone extending substantially uniformly across the composite's width and along the
composite's length; and

the second transition zone comprising ~~fibers from the second and third strata commingled~~
a substantially uniform mixture of second fibers, superabsorbent material, and third fibers, the
transition zone extending substantially uniformly across the composite's width and along the
composite's length.

2. (Original) The composite of Claim 1, wherein first fibers are at least one of synthetic fibers, matrix fibers, and resilient fibers.

3. (Original) The composite of Claim 1, wherein second fibers are at least one of matrix fibers and resilient fibers.

4. (Original) The composite of Claim 1, wherein third fibers are at least one of synthetic fibers, matrix fibers, and resilient fibers.

LAW OFFICES OF
CHRISTENSEN O'CONNOR JOHNSON KINDNESS^{PLLC}
1420 Fifth Avenue
Suite 2800
Seattle, Washington 98101
206.682.8100

5. (Original) The composite of Claim 1, wherein the first fibers comprises synthetic fibers, the second fibers comprise matrix and resilient fibers, and the third fibers comprise synthetic fibers.

6. (Original) The composite of Claim 1, wherein the first fibers comprises synthetic fibers, the second fibers comprise matrix and resilient fibers, and the third fibers comprise matrix and resilient fibers.

7. (Original) The composite of Claim 1, wherein the first fibers comprises matrix and resilient fibers, the second fibers comprise matrix and resilient fibers, and the third fibers comprise matrix and resilient fibers.

8. (Original) The composite of Claim 2, wherein the resilient fibers comprise fibers selected from the group consisting of chemically stiffened fibers, anfractuous fibers, chemithermomechanical pulp fibers, prehydrolyzed kraft pulp fibers, synthetic fibers, and mixtures thereof.

9. (Original) The composite of Claim 8, wherein the chemically stiffened fibers comprise crosslinked cellulosic fibers.

10. (Original) The composite of Claim 2, wherein the synthetic fibers comprise fibers selected from the group consisting of polyolefin, polyester, polyamide, and thermobondable fibers.

11. (Original) The composite of Claim 10, wherein the polyester fibers comprise polyethylene terephthalate fibers.

12. (Original) The composite of Claim 2, wherein the matrix fibers comprise cellulosic fibers.

13. (Original) The composite of Claim 12, wherein the cellulosic fibers comprise fibers selected from the group consisting of wood pulp fibers, cotton linters, cotton fibers, hemp fibers, rayon fibers, cellulose acetate fibers, and mixtures thereof.

14. (Original) The composite of Claim 1, wherein one or more strata further comprises a binder.

15. (Original) The composite of Claim 14, wherein the binder is selected from the group consisting of thermoplastic fibers, soluble bonding mediums, and wet strength agents.

16. (Original) The composite of Claim 14, wherein the binder comprises bicomponent binding fibers.

17. (Original) The composite of Claim 14, wherein the binder comprises a wet strength agent.

18. (Original) The composite of Claim 17, wherein the binder comprises a polyamide-epichlorohydrin resin.

19. (Canceled)

20. (Original) The composite of Claim 1, wherein the first stratum has a basis weight in the range from about 20 to about 80 gsm.

21. (Original) The composite of Claim 1, wherein the first stratum comprises polyethylene terephthalate fibers and bicomponent binding fibers.

22. (Original) The composite of Claim 21, wherein the polyethylene terephthalate fibers are present in the stratum in an amount from about 70 to about 90 percent by weight based on the total weight of fibers in the stratum.

23. (Original) The composite of Claim 21, wherein the bicomponent binding fibers are present in the stratum in an amount from about 10 to about 30 percent by weight based on the total weight of fibers in the stratum.

24. (Original) The composite of Claim 1, wherein the first stratum has a basis weight of about 50 gsm and comprises about 80 percent by weight polyethylene terephthalate fibers and about 20 percent by weight bicomponent binding fibers based on the total weight of fibers in the stratum.

25. (Original) The composite of Claim 1, wherein the first stratum comprises matrix fibers and resilient fibers.

26. (Original) The composite of Claim 1, wherein the first stratum comprises wood pulp fibers and crosslinked cellulosic fibers.

27. (Original) The composite of Claim 26, wherein the wood pulp fibers are present in the stratum in an amount from about 20 to about 80 percent by weight based on the total weight of fibers in the stratum.

28. (Original) The composite of Claim 26, wherein the crosslinked cellulosic fibers are present in the stratum in an amount from about 20 to about 80 percent by weight based on the total weight of fibers in the stratum.

29. (Original) The composite of Claim 1, wherein the first stratum has a basis weight of about 40 gsm and comprises about 40 percent by weight wood pulp fibers and about 60 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

30. (Original) The composite of Claim 1, wherein the first stratum has a basis weight of about 40 gsm and comprises about 50 percent by weight wood pulp fibers and about 50 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

31. (Original) The composite of Claim 1, wherein the first stratum has a basis weight of about 20 gsm and comprises about 50 percent by weight wood pulp fibers and about

LAW OFFICES OF
CHRISTENSEN O'CONNOR JOHNSON KINDNESS^{PLLC}
1420 Fifth Avenue
Suite 2800
Seattle, Washington 98101
206.682.8100

50 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

32. (Original) The composite of Claim 1, wherein the second stratum comprises matrix fibers and resilient fibers.

33. (Original) The composite of Claim 1, wherein the second stratum comprises wood pulp fibers and crosslinked cellulosic fibers.

34. (Original) The composite of Claim 33, wherein the wood pulp fibers are present in the stratum in an amount from about 30 to about 80 percent by weight based on the total weight of fibers in the stratum.

35. (Original) The composite of Claim 33, wherein the crosslinked cellulosic fibers are present in the stratum in an amount from about 20 to about 70 percent by weight based on the total weight of fibers in the stratum.

36. (Original) The composite of Claim 1, wherein the second stratum comprises about 30 percent by weight wood pulp fibers and about 70 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

37. (Original) The composite of Claim 1, wherein the second stratum comprises about 40 percent by weight wood pulp fibers and about 60 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

38. (Original) The composite of Claim 1, wherein the second stratum comprises about 50 percent by weight wood pulp fibers and about 50 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

39. (Original) The composite of Claim 1, wherein the second stratum comprises about 70 percent by weight wood pulp fibers and about 30 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

40. (Original) The composite of Claim 1, wherein the second stratum comprises about 75 percent by weight wood pulp fibers and about 25 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

41. (Previously presented) The composite of Claim 1, wherein the second stratum comprises from about 20 to about 80 percent by weight superabsorbent material based on the total weight of the stratum.

42. (Previously presented) The composite of Claim 1, wherein the second stratum comprises about 25 percent by weight superabsorbent material based on the total weight of the stratum.

43. (Previously presented) The composite of Claim 1, wherein the second stratum comprises about 30 percent by weight superabsorbent material based on the total weight of the stratum.

44. (Previously presented) The composite of Claim 1, wherein the second stratum comprises about 40 percent by weight superabsorbent material based on the total weight of the stratum.

45. (Previously presented) The composite of Claim 1, wherein the second stratum comprises about 45 percent by weight superabsorbent material based on the total weight of the stratum.

46. (Previously presented) The composite of Claim 1, wherein the second stratum comprises about 55 percent by weight superabsorbent material based on the total weight of the stratum.

47. (Previously presented) The composite of Claim 1, wherein the second stratum comprises about 60 percent by weight superabsorbent material based on the total weight of the stratum.

48. (Original) The composite of Claim 1, wherein the third stratum has a basis weight in the range from about 20 to about 80 gsm.

49. (Original) The composite of Claim 1, wherein the third stratum comprises polyethylene terephthalate fibers and bicomponent binding fibers.

50. (Original) The composite of Claim 49, wherein the polyethylene terephthalate fibers are present in the stratum in an amount from about 70 to about 90 percent by weight based on the total weight of fibers in the stratum.

51. (Original) The composite of Claim 49, wherein the bicomponent binding fibers are present in the stratum in an amount from about 10 to about 30 percent by weight based on the total weight of fibers in the stratum.

52. (Original) The composite of Claim 1, wherein the third stratum has a basis weight of about 20 gsm and comprises about 80 percent by weight polyethylene terephthalate fibers and about 20 percent by weight bicomponent binding fibers based on the total weight of fibers in the stratum.

53. (Original) The composite of Claim 1, wherein the third stratum comprises matrix fibers and resilient fibers.

54. (Original) The composite of Claim 1, wherein the third stratum comprises wood pulp fibers and crosslinked cellulosic fibers.

55. (Original) The composite of Claim 54, wherein the wood pulp fibers are present in the stratum in an amount from about 30 to about 80 percent by weight based on the total weight of fibers in the stratum.

56. (Original) The composite of Claim 54, wherein the crosslinked cellulosic fibers are present in the stratum in an amount from about 20 to about 70 percent by weight based on the total weight of fibers in the stratum.

57. (Original) The composite of Claim 1, wherein the third stratum has a basis weight of about 30 gsm and comprises about 50 percent by weight wood pulp fibers and about 50 percent by weight crosslinked cellulosic fibers based on the total weight of fibers in the stratum.

58. (Original) The composite of Claim 1, wherein the third stratum has a basis weight of about 30 gsm and comprises about 75 percent by weight crosslinked cellulosic fibers and about 25 percent by weight of a refined blend of wood pulp fibers and crosslinked fibers based on the total weight of fibers in the stratum.

59. (Currently amended) An absorbent composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata;

the first stratum comprising polyethylene terephthalate fibers and bicomponent binder fibers;

the second stratum comprising wood pulp fibers, crosslinked cellulosic fibers, and superabsorbent material;

the third stratum comprising polyethylene terephthalate fibers and bicomponent binder fibers;

the first transition zone comprising ~~fibers from the first and second strata commingled a~~ substantially uniform mixture of polyethylene terephthalate fibers, bicomponent binder fibers, wood pulp fibers, crosslinked cellulosic fibers, and superabsorbent material, the transition zone extending substantially uniformly across the composite's width and along the composite's length; and

the second transition zone comprising ~~fibers from the second and third strata commingled~~
a substantially uniform mixture of polyethylene terephthalate fibers, bicomponent binder fibers,
wood pulp fibers, crosslinked cellulosic fibers, and superabsorbent material, the transition zone
extending substantially uniformly across the composite's width and along the composite's length.

60. (Currently amended) An absorbent composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata;

the first stratum comprising polyethylene terephthalate fibers and bicomponent binder fibers;

the second stratum comprising wood pulp fibers, crosslinked cellulosic fibers, and superabsorbent material;

the third stratum comprising wood pulp fibers and crosslinked cellulosic fibers;

the first transition zone comprising ~~fibers from the first and second strata commingled~~ a
substantially uniform mixture of polyethylene terephthalate fibers, bicomponent binder fibers,
wood pulp fibers, crosslinked cellulosic fibers, and superabsorbent material, the transition zone
extending substantially uniformly across the composite's width and along the composite's length;
and

the second transition zone comprising ~~fibers from the second and third strata commingled~~
a substantially uniform mixture of wood pulp fibers, crosslinked cellulosic fibers, and
superabsorbent material, the transition zone extending substantially uniformly across the
composite's width and along the composite's length.

61. (Currently amended) An absorbent composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first

LAW OFFICES OF
CHRISTENSEN O'CONNOR JOHNSON KINDNESS^{PLLC}
1420 Fifth Avenue
Suite 2800
Seattle, Washington 98101
206.682.8100

and second strata, and a second transition zone intermediate and coextensive with the second and third strata;

the first stratum comprising wood pulp fibers and crosslinked cellulosic fibers;

the second stratum comprising wood pulp fibers, crosslinked cellulosic fibers, and superabsorbent material;

the third stratum comprising wood pulp fibers and crosslinked cellulosic fibers;

the first transition zone comprising ~~fibers from the first and second strata commingled a~~
substantially uniform mixture of wood pulp fibers, crosslinked cellulosic fibers, and
superabsorbent material, the transition zone extending substantially uniformly across the
composite's width and along the composite's length; and

the second transition zone comprising ~~fibers from the second and third strata commingled~~
a substantially uniform mixture of wood pulp fibers, crosslinked cellulosic fibers, and
superabsorbent material, the transition zone extending substantially uniformly across the
composite's width and along the composite's length.

62. (Original) An absorbent article comprising the composite of Claim 1.
63. (Original) An absorbent article comprising the composite of Claim 5.
64. (Original) An absorbent article comprising the composite of Claim 6.
65. (Original) An absorbent article comprising the composite of Claim 7.
66. (Original) An absorbent article comprising the composite of Claim 21.
67. (Original) An absorbent article comprising the composite of Claim 25.
68. (Original) An absorbent article comprising the composite of Claim 32.
69. (Original) An absorbent article comprising the composite of Claim 49.
70. (Original) An absorbent article comprising the composite of Claim 54.
71. (Original) An absorbent article comprising the composite of Claim 59.

LAW OFFICES OF
CHRISTENSEN O'CONNOR JOHNSON KINDNESS^{PLLC}
1420 Fifth Avenue
Suite 2800
Seattle, Washington 98101
206.682.8100

72. (Original) An absorbent article comprising the composite of Claim 60.
73. (Original) An absorbent article comprising the composite of Claim 61.
74. (Original) The composite of Claim 1, wherein the composite is folded into a C-shaped configuration.
75. (Original) The composite of Claim 59, wherein the composite is folded into a C-shaped configuration.
76. (Original) The composite of Claim 60, wherein the composite is folded into a C-shaped configuration.
77. (Original) The composite of Claim 61, wherein the composite is folded into a C-shaped configuration.
78. (Currently amended) An absorbent construct, comprising a first composite and a second composite, each composite comprising first, second, and third strata, and each composite having first and second surfaces, wherein each first surface is the outward surface of the first stratum and each second surface is the outward surface of the third stratum, and wherein the second surface of the first composite is coextensive with at least a portion of the first surface of the second composite,
- the first composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata;
- the first stratum comprising synthetic fibers and a binder;
- the second stratum comprising matrix fibers, resilient fibers, and superabsorbent material;
- the third stratum comprising matrix fibers and resilient fibers;
- the first transition zone comprising ~~fibers from the first and second strata commingled a~~
substantially uniform mixture of synthetic fibers, binder, matrix fibers, resilient fibers, and

superabsorbent material, the transition zone extending substantially uniformly across the composite's width and along the composite's length; and

the second transition zone comprising ~~fibers from the second and third strata commingled~~
a substantially uniform mixture of matrix fibers, resilient fibers, and superabsorbent material, the
transition zone extending substantially uniformly across the composite's width and along the composite's length; and

the second composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata;

the first stratum comprising matrix fibers and resilient fibers;

the second stratum comprising matrix fibers, resilient fibers, and superabsorbent material;

the third stratum comprising matrix fibers and resilient fibers;

the first transition zone comprising ~~fibers from the first and second strata commingled~~ a
substantially uniform mixture of matrix fibers, resilient fibers, and superabsorbent material, the
transition zone extending substantially uniformly across the composite's width and along the composite's length; and

the second transition zone comprising ~~fibers from the second and third strata commingled~~
a substantially uniform mixture of matrix fibers, resilient fibers, and superabsorbent material, the
transition zone extending substantially uniformly across the composite's width and along the composite's length.

79. (Currently amended) An absorbent construct, comprising a first composite and a second composite, each composite comprising first, second, and third strata, and each composite having first and second surfaces, wherein each first surface is the outward surface of the first stratum and each second surface is the outward surface of the third stratum, and wherein the

LAW OFFICES OF
CHRISTENSEN O'CONNOR JOHNSON KINDNESS^{PLLC}
1420 Fifth Avenue
Suite 2800
Seattle, Washington 98101
206.682.8100

second surface of the first composite is coextensive with at least a portion of the first surface of the second composite,

the first composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata;

the first stratum comprising synthetic fibers and a binder;

the second stratum comprising matrix fibers, resilient fibers, and superabsorbent material;

the third stratum comprising matrix fibers and resilient fibers;

the first transition zone comprising ~~fibers from the first and second strata commingled a~~ substantially uniform mixture of synthetic fibers, binder, matrix fibers, resilient fibers, and superabsorbent material, the transition zone extending substantially uniformly across the composite's width and along the composite's length; and

the second transition zone comprising ~~fibers from the second and third strata commingled a~~ substantially uniform mixture of matrix fibers, resilient fibers, and superabsorbent material, the transition zone extending substantially uniformly across the composite's width and along the composite's length; and

the second composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata;

the first stratum comprising matrix fibers and resilient fibers;

the second stratum comprising matrix fibers, resilient fibers, and superabsorbent material;

the third stratum comprising synthetic fibers and binder;

the first transition zone comprising ~~fibers from the first and second strata commingled a~~ substantially uniform mixture of matrix fibers, resilient fibers, and superabsorbent material, the

transition zone extending substantially uniformly across the composite's width and along the composite's length; and

the second transition zone comprising ~~fibers from the second and third strata commingled~~
a substantially uniform mixture of synthetic fibers, binder, matrix fibers, resilient fibers, and
superabsorbent material, the transition zone extending substantially uniformly across the composite's width and along the composite's length.

80-107. (Canceled)

108. (Currently amended) An absorbent composite comprising a first stratum, a second stratum, a third stratum, a first transition zone intermediate and coextensive with the first and second strata, and a second transition zone intermediate and coextensive with the second and third strata, the first stratum comprising first fibers, the second stratum comprising second fibers and superabsorbent material, the third stratum comprising third fibers, the first transition zone comprising ~~fibers from the first and second strata commingled~~ first fibers, second fibers, and
superabsorbent material, the transition zone extending substantially uniformly across the composite's width and along the composite's length, and the second transition zone comprising ~~fibers from the second and third strata commingled~~ second fibers, superabsorbent material, and
third fibers, the transition zone extending substantially uniformly across the composite's width and along the composite's length, obtainable by the process of:

- (a) introducing a first furnish into a first chamber of a divided headbox, wherein the first furnish comprises first fibers;
- (b) introducing a second furnish into a second chamber of a divided headbox, wherein the second furnish comprises second fibers and superabsorbent material;

(c) introducing a third furnish into a third chamber of a divided headbox, wherein the third furnish comprises third fibers, and wherein the second chamber is intermediate the first chamber and the third chamber;

(d) flowing the first furnish from the first chamber into contact with a first foraminous support;

(e) flowing the third furnish from the third chamber into contact with a second foraminous support;

(f) flowing the second furnish from the second chamber between the first and third furnishes, wherein at least a portion of the fibers of the second furnish mix with the fibers of the first furnish, and wherein at least a portion of the fibers of the second furnish mix with the fibers of the second furnish; and

(g) dewatering the furnishes flowed into contact with the foraminous supports to provide the composite.

LAW OFFICES OF
CHRISTENSEN O'CONNOR JOHNSON KINDNESS^{PLLC}
1420 Fifth Avenue
Suite 2800
Seattle, Washington 98101
206.682.8100